



PRIME SERIES CHARCOAL NR 2-PLY AUTOMOTIVE WINDOW FILMS



The Clear Vision in Solar Protection®

LIFETIME WARRANTY

BENEFITS TO INSTALLATION

- Very aggressive adhesive eliminates fingering
- Great optical clarity with no distortion
- Reliable unmatched scratch-resistant coating
- Static-free makes it plotter friendly

Series	VLT	10" Visor	20"	24"	36"	40"	60" x 100'
PRIME SERIES CHARCOAL	5%, 20%, 35%, 50%						

A charcoal film with a classic, neutral tone. The Prime Series is a deep dyed 2-ply, 1.5 Mil polyester film that will provide minimal color fade over time and will hold up beautifully in any climate. The charcoal counterpart to Vintage, this film will improve installation time and increase productivity. VLTs available: 5%, 20%, 35% and 50%.

Charcoal NR Automotive Window Films	VLT	VLR	TSEt	TSEr	TSEa	UVR	TSEr	GR
PRIME 05	4	6	41	5	54	99	42	95
PRIME 20	18	6	48	5	47	99	40	79
PRIME 35	35	6	54	6	40	99	36	63
PRIME 50	49	6	58	6	36	99	30	50

VLT = Visible Light Transmission
VLR = Visible Light Reflectance (Int)

TSEt = Total Solar Transmittance
TSEa = Total Solar Absorbance

TSEr = Total Solar Reflectance
UVR = Ultraviolet Rejected

GR = Glare Reduction
TSEr = Total Solar Energy Rejected

PREMIUM LIFETIME WARRANTY

BENEFITS TO INSTALLATION

- Very aggressive adhesive eliminates fingering
- Great optical clarity with no distortion
- Reliable unmatched scratch-resistant coating
- Static-free makes it plotter friendly

ULTRAFX SERIES CHARCOAL COLOR-STABLE NR 2-PLY AUTOMOTIVE WINDOW FILMS



Series	VLT	10" Visor	20"	24"	36"	40"	60" x 100'
ULTRAFX SERIES CHARCOAL	5%, 15%, 20%, 30%, 35%, 40%, 50%, 55%, 70%						

A color-stable classic charcoal film that features a clean, neutral tone. The Ultra Series is a deep dyed 2-ply, 1.5 Mil polyester film in which UV inhibitors are utilized at multiple stages of the manufacturing process, ensuring the dyes will retain their color for years to come. This is the film of all films, try it and nothing else will compare. VLTs available: 5%, 15%, 20%, 30%, 35%, 40%, 50%, 55% and 70%.

Charcoal NR Automotive Window Films	VLT	VLR	TSEt	TSEr	TSEa	UVR	TSEr	GR
ULTRA 05	5	6	36	5	59	99	42	95
ULTRA 15	15	6	43	5	51	99	41	83
ULTRA 20	18	6	45	5	50	99	40	80
ULTRA 30	31	6	51	5	44	99	36	68
ULTRA 35	34	6	53	6	41	99	35	61
ULTRA 40	41	6	55	5	40	99	34	57
ULTRA 50	48	6	58	6	36	99	30	50
ULTRA 55	55	6	62	6	32	99	29	40
ULTRA 70	70	7	68	7	25	99	23	22

VLT = Visible Light Transmission
VLR = Visible Light Reflectance (Int)

TSEt = Total Solar Transmittance
TSEa = Total Solar Absorbance

TSEr = Total Solar Reflectance
UVR = Ultraviolet Rejected

GR = Glare Reduction
TSEr = Total Solar Energy Rejected